



HEIDELBERGCEMENT Group

Tanzania Portland Cement Public Limited Company

P.O.Box 1950, Dar es Salaam-Tanzania

Telephone: +255 746 810930

Fax: +255 746 810931

Info@twigacement.com

www.twigacement.com

MONTHLY CERTIFICATE OF CHEMICAL & PHYSICAL TESTS TWIGA PLUS, CEM II/B-L CLASS 42.5 N JUNE, 2023

Sampled and tested in accordance with the requirements of the Tanzanian Bureau of Standards

TZS 727-1/EAS 18-1

CHEMICAL TEST RESULTS			
Test	Unit	Test results	Specified requirements
Loss on Ignition	[%]	9.4	No requirement
Insoluble residue	[%]	1.2	Less than 5.0%
CaO	[%]	58.8	No requirement
SiO ₂	[%]	18.3	No requirement
CaO/SiO ₂	[-]	3.2	Not less than 2.0%
Al ₂ O ₃	[%]	4.9	No requirement
Fe ₂ O ₃	[%]	2.8	No requirement
MgO	[%]	0.7	Not more than 5.0%
SO ₃	[%]	2.6	Less than 3.5%
K ₂ O	[%]	0.3	No requirement
Na ₂ O	[%]	0.2	No requirement
P ₂ O ₅	[%]	0.1	No requirement
TiO ₂	[%]	0.3	No requirement
MnO	[%]	0.1	No requirement
(Na ₂ O+ 0.658K ₂ O)	[%]	0.4	No requirement
Cl	[%]	0.001	Less than 0.10%
PHYSICAL TEST RESULTS			
Density	[kg/m ³]	3000	No requirement
Specific Surface (Blaine)	[m ² /kg]	442	No requirement
Sieving Residue on 45 mic. mesh	[%]	9.5	No requirement
Initial Setting Time	[Minutes]	120	Not less than 60 minutes
Soundness (Expansion)	[mm]	1.0	Not more than 10.0 mm
Compressive Strength 2 days	[MPa]	17.5	More than 10.0 MPa
Compressive Strength 28 days*	[MPa]	44.5	Between 42.5 and 62.5 Mpa

Remarks: * The 28 days strength is the average of previous month.

Wazo Hill, 2023/07/22th


Quality Control Manager


Plant Manager


Commercial Director

Board Directors:
Hakan Gurdal (Turkish)
Alfonso Velez (Spanish)
Francesco Brambilla (Italian)

Ruth Zaipuna (Tanzanian)
Gary Whitehead (British)
Oswald Urassa (Tanzanian)