



HEIDELBERGCEMENT Group

Tanzania Portland Cement Public Limited Company  
P.O.Box 1950, Dar es Salaam-Tanzania

Telephone: +255-746 810 930

Fax: +255-746 810 931

[Info@twigacement.com](mailto:Info@twigacement.com)

[www.twigacement.com](http://www.twigacement.com)

## MONTHLY CERTIFICATE OF CHEMICAL AND PHYSICAL TESTS TWIGA ORDINARY, CEM I CLASS 42.5 N

### SEPTEMBER, 2023

Sampled and tested in accordance with the requirements of the Tanzanian Bureau of Standards

TZS 727-1/EAS 18-1

CHEMICAL TEST RESULTS			
Test	Unit	Test results monthly average	Specified requirements
Loss on ignition	[%]	4.7	Less than 5.0%
Insoluble residue	[%]	1.0	Less than 5.0%
CaO	[%]	60.1	No Requirement
SiO <sub>2</sub>	[%]	20.2	No Requirement
CaO/SiO <sub>2</sub>	[-]	3.0	Not less than 2.0%
Al <sub>2</sub> O <sub>3</sub>	[%]	5.4	No Requirement
Fe <sub>2</sub> O <sub>3</sub>	[%]	3.2	No Requirement
MgO	[%]	1.0	Not more than 5.0%
SO <sub>3</sub>	[%]	2.4	Less than 3.5%
K <sub>2</sub> O	[%]	0.38	No Requirement
Na <sub>2</sub> O	[%]	0.13	No Requirement
P <sub>2</sub> O <sub>5</sub>	[%]	0.08	No Requirement
TiO <sub>2</sub>	[%]	0.39	No Requirement
MnO	[%]	0.05	No Requirement
(Na <sub>2</sub> O+0.658K <sub>2</sub> O)	[%]	0.38	No Requirement
Cl <sup>-</sup>	[%]	0.001	Less than 0.10%
PHYSICAL TEST RESULTS			
Density	[kg/m <sup>3</sup> ]	3000	No requirement
Specific Surface (Blaine)	[m <sup>2</sup> /kg]	359	No Requirement
Sieving Residue on 45 mic.	[%]	13.6	No Requirement
Initial setting time	[minutes]	120	Not less than 60 minutes
Soundness (expansion)	[mm.]	1.0	Not more than 10 mm.
Compressive strength 2 days	[MPa]	21.1	More than 10 MPa.
Compressive strength 28 days*	[MPa]	50.0	Between 42.5 and 62.5 MPa

Remarks: \*The 28 days strength is the average of previous month.

Wazo Hill, 2023/10/06<sup>th</sup>

  
Quality Control Manager

  
Plant Manager

  
Commercial Director

Board Directors:  
Hakan Gurdal (Turkish)  
Alfonso Velez (Spanish)  
Francesco Brambilla (Italian)

Ruth Zaipuna (Tanzanian)  
Gary Whitehead (British)  
Oswald Urassa (Tanzanian)