

## **HEIDELBERG**CEMENT Group

## Tanzania Portland Cement Public Limited Company P.O.Box 1950,Dar es Salaam-Tanzania

Telephone: +255 746 810930 Fax: +255 746 810931

## www.twigacement.com

## MONTHLY CERTIFICATE OF CHEMICAL AND PHYSICAL TESTS TWIGA EXTRA, CEM II/B-L CLASS 32.5 R

NOVEMBER, 2023

Sampled and tested in accordance with the requirements of the Tanzanian Bureau of Standards

TZS 727-1/EAS 18-1

	CHEMICA	L TEST RESULTS	
Test	Unit	Test results monthly average	Specified requirements
Loss on ignition	[%]	12.4	No Requirement
Insoluble Residue	[%]	1.2	Less than 5.0%
CaO	[%]	57.2	No Requirement
SiO <sub>2</sub>	[%]	18.3	No Requirement
CaO/SiO <sub>2</sub>	[-]	3.1	Not less than 2.0%
Al <sub>2</sub> O <sub>3</sub>	[%]	4.6	No Requirement
Fe <sub>2</sub> O <sub>3</sub>	[%]	3.0	No Requirement
MgO	[%]	1.0	Not more than 5.0%
SO <sub>3</sub>	[%]	2.7	Less than 3.5%
K <sub>2</sub> O	[%]	0.38	No Requirement
Na <sub>2</sub> O	[%]	0.10	No Requirement
P <sub>2</sub> O <sub>5</sub>	[%]	0.08	No Requirement
TiO <sub>2</sub>	[%]	0.38	No Requirement
MnO	[%]	0.05	No Requirement
(Na <sub>2</sub> O+0.658K <sub>2</sub> O)	[%]	0.34	No Requirement
Cl	[%]	0.002	Less than 0.10%
		L TEST RESULTS	A SECTION OF THE PROPERTY OF T
Density	[kg/m³]	3100	No requirement
Specific Surface (Blaine)	[m²/kg]	457	No Requirement
Sieving Residue on 45 mic.	[%]	8.2	No Requirement
Initial setting time	[minutes]	129	Not less than 75 minutes
Soundness (expansion)	[mm.]	1.0	Not more than 10 mm.
Compressive strength 2 days	[MPa]	14.5	More than 10 MPa.
Compressive strength 28 days*	[MPa]	34.5	Between 32.5 and 52.5 MPa

Remarks: \*The 28 days strength is the average of previous month.

Wazo Hill, 2023/12/06th

Quality Control Manager

Board Directors: Hakan Gurdal (Turkish) Alfonso Velez (Spanish) Francesco Brambilla (Italian)

Ruth Zaipuna (Tanzanian) Gary Whitehead (British) Oswald Urassa (Tanzanian)

Plant Manager

Commercial Director