



Heidelberg Materials

Tanzania Portland Cement Public Limited Company

P.O.Box 1950, Dar es Salaam-Tanzania

Telephone: +255-746 810 930

Fax: +255-746 810 931

[Info@twigacement.com](mailto:Info@twigacement.com)

[www.twigacement.com](http://www.twigacement.com)

## MONTHLY CERTIFICATE OF CHEMICAL & PHYSICAL TESTS

### TWIGA MEGA CEM III/B-SR CLASS 42.5N

FEBRUARY, 2025

Sampled and tested in accordance with the requirements of the Tanzanian Bureau of Standards

**TZS 727-1/ EAS 18-1. Equivalent to EN 197-1**

CHEMICAL TEST RESULTS			
Test	Unit	Test results	Specified requirements
Loss on Ignition	[%]	2.94	No requirement
Insoluble Residues	[%]	1.04	Less than 5.0%
CaO	[%]	47.7	No requirement
SiO <sub>2</sub>	[%]	26.8	No requirement
CaO/SiO <sub>2</sub>	[-]	1.77	Not less than 2.0%
Al <sub>2</sub> O <sub>3</sub>	[%]	9.76	No requirement
Fe <sub>2</sub> O <sub>3</sub>	[%]	2.49	No requirement
MgO	[%]	4.81	Not more than 5.0%
SO <sub>3</sub>	[%]	2.76	Less than 3.5%
K <sub>2</sub> O	[%]	0.34	No requirement
Na <sub>2</sub> O	[%]	0.19	No requirement
P <sub>2</sub> O <sub>5</sub>	[%]	0.20	No requirement
MnO	[%]	0.12	No requirement
TiO <sub>2</sub>	[%]	0.65	No requirement
(Na <sub>2</sub> O+ 0.658K <sub>2</sub> O)	[%]	0.41	No requirement
Cl <sup>-</sup>	[%]	0.001	Less than 0.10%
PHYSICAL TEST RESULTS			
Density	[kg/m <sup>3</sup> ]	3102	No requirement
Specific Surface (Blaine)	[m <sup>2</sup> /kg]	474	No requirement
Sieving Residue on 45 mic.	[%]	5.7	No requirement
Initial Setting Time	[Minutes]	195	Not less than 60 minutes
Final Setting Time	[Minutes]	252	No requirement
Soundness (Expansion)	[mm]	1.0	Not more than 10.0 mm
Compressive Strength 2 days	[MPa]	11.5	More than 10.0 MPa
Compressive Strength 7 days	[MPa]	29.6	No requirement
Compressive Strength 28 days*	[MPa]	50.3	Between 42.5 and 62.5 MPa

Remarks: \* The 28 days strength is the average of previous month

Wazo Hill, 2025/03/04<sup>th</sup>

Quality Control Manager

Plant Manager

Commercial Director

Head Office  
P.O. Box 1950, Dar es Salaam  
Tanzania  
Tel: +255 746 810 930  
Fax: +255 746 810 931

Head Office  
P.O. Box 1950, Dar es Salaam  
Tanzania  
Tel: +255 746 810 930  
Fax: +255 746 810 931