

Tanzania Portland Cement Company limited

P.O.Box 1950, Dar es Salaam-Tanzania

Telephone: +255-784108600 Fax: +255-784108609 Info@twigacement.com www.twigacement.com

WEEKLY CERTIFICATE OF CHEMICAL & PHYSICAL TESTS

TWIGA EXTRA, CEM II/B-L CLASS 32.5 R

Average of dispatched cement during week 12/2017 (from 20th March, 2017 to 26th March, 2017) Sampled and tested in accordance with the requirements of the Tanzanian standard

TZS727:2002. Equivalent to EN 197-1

| Test | Unit | Test results | Specified requirements TZS 727:2002 |
|-------------------------------|----------------------|--------------|--|
| Loss on Ignition | [%] | 14.3 | No requirement |
| Insoluble Residues | [%] | 1.3 | Less than 5.0% |
| CaO | [%] | 61.6 | No requirement |
| SiO ₂ | [%] | 15.9 | No requirement |
| CaO/SiO ₂ | [-] | 3.9 | Not less than 2.0% |
| Al_2O_3 | [%] | 4.1 | No requirement |
| Fe_2O_3 | [%] | 2.4 | No requirement |
| MgO | [%] | 0.4 | Not more than 5.0% |
| SO ₃ | [%] | 2.6 | Less than 3.5% |
| Cl. | [%] | 0.001 | Less than 0.10% |
| Density | [kg/m ³] | 3000 | No requirement |
| Specific Surface (Blaine) | $[m^2/kg]$ | 474 | No requirement |
| Sieving Residue on 45 mic. | [%] | 12.3 | No requirement |
| Initial Setting Time | [Minutes] | 145 | Not less than 75 minutes |
| Soundness (Expansion) | [mm] | 1.0 | Not more than 10.0 mm |
| Compressive Strength 2 days | [MPa] | 14.4 | More than 10.0 MPa |
| Compressive Strength 28 days* | [MPa] | 36.6 | Between 32.5 and 52.5 Mpa |

Remarks: * Cement dispatched during week 08/2017 (from 20th February, 2017 to 26th February, 2017)

Wazo Hill, 2017/03/30th

Quality Control Manager

Quality & Process Control Manager

Commercial Director

SIMON DELENS

Board Directors: Jean-Marc Junon (French) Alfonso Rodriguez (Spanish) Hakan Gurdal (Turkish)

Gary Whitehead (British) Ruth Zaipuna (Tanzanian) Oswald Urassa (Tanzanian)