



Heidelberg Materials

Tanzania Portland Cement Public Limited Company
P.O.Box 1950, Dar es Salaam-Tanzania
Telephone: +255 746 810930
Fax: +255 746 810931
Info@twigacement.com
www.twigacement.com

MONTHLY CERTIFICATE OF CHEMICAL & PHYSICAL TESTS

TWIGA PLUS, CEM II/B-M CLASS 42.5 N

MARCH, 2025

Sampled and tested in accordance with the requirements of the Tanzanian Bureau of Standards

TZS 727-1/EAS 18-1. Equivalent to EN 197-1

CHEMICAL TEST RESULTS			
Test	Unit	Test results	Specified requirements
Loss on Ignition	[%]	7.36	No requirement
Insoluble Residues	[%]	1.44	Less than 5.0%
CaO	[%]	54.7	No requirement
SiO ₂	[%]	20.8	No requirement
CaO/SiO ₂	[-]	2.63	Not less than 2.0%
Al ₂ O ₃	[%]	5.72	No requirement
Fe ₂ O ₃	[%]	3.92	No requirement
MgO	[%]	1.34	Not more than 5.0%
SO ₃	[%]	2.52	Less than 3.5%
K ₂ O	[%]	0.45	No requirement
Na ₂ O	[%]	0.18	No requirement
P ₂ O ₅	[%]	0.48	No requirement
TiO ₂	[%]	0.65	No requirement
MnO	[%]	0.14	No requirement
(Na ₂ O + 0.658 K ₂ O)	[%]	0.54	No requirement
Cl ⁻	[%]	0.001	Less than 0.10%
PHYSICAL TEST RESULTS			
Density	[kg/m ³]	3100	No requirement
Specific Surface (Blaine)	[m ² /kg]	454	No requirement
Sieving Residue on 45 mic. mesh	[%]	8.5	No requirement
Initial Setting Time	[Minutes]	148	Not less than 60 minutes
Final Setting Time	[Minutes]	215	No requirement
Soundness (Expansion)	[mm]	1.0	Not more than 10.0 mm
Compressive Strength 2 days	[MPa]	17.6	More than 10.0 MPa
Compressive Strength 28* *days*	[MPa]	44.6	Between 42.5 and 62.5 Mpa

Remarks: * The 28 days strength is the average of previous month.

Wazo Hill, 2025/04/04th

Quality Control Manager

Plant Manager

Commercial Director

Board Directors:
Hakan Gurdal (Turkish)
Alfonso Velez (Spanish)
Francesco Brambilla (Italian)

Ruth Zaipuna (Tanzanian)
Gary Whitehead (British)
Oswald Urassa (Tanzanian)