

## Heidelberg Materials

## **Tanzania Portland Cement Public Limited Company**

P.O.Box 1950, Dar es Salaam-Tanzania

Telephone: +255 746 810930 Fax: +255 746 810931 Info@twigacement.com www.twigacement.com

## MONTHLY CERTIFICATE OF CHEMICAL AND PHYSICAL TESTS TWIGA EXTRA, CEM II/B-L CLASS 32.5 R JUNE, 2025 Sampled and tested in accordance with the requirements of the Tanzanian Bureau of Standards

TZS 727-1/EAS 18-1. Equivalent to EN 197-1

	CHEMICA	L TEST RESULTS	
Test	Unit	Test results monthly average	Specified requirements
Loss on ignition	[%]	11.5	No Requirement
Insoluble Residue	[%]	1.22	Less than 5.0%
CaO	[%]	56.0	No Requirement
SiO <sub>2</sub>	[%]	19.3	No Requirement
CaO/SiO <sub>2</sub>	[-]	2.90	Not less than 2.0%
Al <sub>2</sub> O <sub>3</sub>	[%]	5.05	No Requirement
Fe <sub>2</sub> O <sub>3</sub>	[%]	3.18	No Requirement
MgO	[%]	1.30	Not more than 5.0%
SO <sub>3</sub>	[%]	2.57	Less than 3.5%
K <sub>2</sub> O	[%]	0.42	No Requirement
Na <sub>2</sub> O	[%]	0.16	No Requirement
P <sub>2</sub> O <sub>5</sub>	[%]	0.44	No Requirement
TiO <sub>2</sub>	[%]	0.54	No Requirement
MnO -	[%]	0.07	No Requirement
(Na <sub>2</sub> O+0.658K <sub>2</sub> O)	[%]	0.44	No Requirement
Cl	[%]	0.002	Less than 0.10%
	PHYSICAL	TEST RESULTS	
Density	[kg/m <sup>3</sup> ]	3100	No requirement
Specific Surface (Blaine)	[m²/kg]	467	No Requirement
Sieving Residue on 45 mic.	[%]	11.5	No Requirement
Initial setting time	[minutes]	159	Not less than 75 minutes
Final setting time	[minutes]	214	Not Requirement
Soundness (expansion)	[mm.]	1.0	Not more than 10 mm.
Compressive strength 2 days	[MPa]	15.5	More than 10 MPa.
Compressive strength 28 days*	[MPa]	35.5	Between 32.5 and 52.5 MPa

Remarks: \*The 28 days strength is the average of previous month.

Wazo Hill, 2025/07/06th

Quality Control Manager

Board Directors: Hakan Gurdal (Turkish)

Alfonso Velez (Spanish)
Francesco Brambilla (Italian)

Plant Manager

Ruth Zaipuna (Tanzanian) Gary Whitehead (British)
Oswald Urassa (Tanzanian) Commercial Director