

Heidelberg Materials

Tanzania Portland Cement Public Limited Company

P.O.Box 1950, Dar es Salaam-Tanzania

Telephone: +255 746 810930 Fax: +255 746 810931 Info@twigacement.com www.twigacement.com

Commercial Director

MONTHLY CERTIFICATE OF CHEMICAL AND PHYSICAL TESTS TWIGA EXTRA, CEM II/B-L CLASS 32.5 R SEPTEMBER, 2025

Sampled and tested in accordance with the requirements of the Tanzanian Bureau of Standards

TZS 727-1/EAS 18-1. Equivalent to EN 197-1

	CHEMICA	L TEST RESULTS	
Test E	Unit	Test results monthly average	Specified requirements
Loss on ignition	[%]	9.33	No Requirement
Insoluble Residue	[%]	1.22	Less than 5.0%
CaO	[%]	57.0	No Requirement
SiO ₂	[%]	19.2	No Requirement
CaO/SiO ₂	[-]	2.97	Not less than 2.0%
Al ₂ O ₃	[%]	5.90	No Requirement
Fe ₂ O ₃	[%]	3.19	No Requirement
MgO	[%]	1.46	Not more than 5.0%
SO ₃	[%]	2.62	Less than 3.5%
K₂O	[%]	0.41	No Requirement
Na ₂ O	[%]	0.06	No Requirement
P ₂ O ₅	[%]	0.45	No Requirement
TiO ₂	[%]	0.62	No Requirement
MnO	[%]	0.04	No Requirement
(Na ₂ O+0.658K ₂ O)	[%]	0.33	No Requirement
Cl	[%]	0.002	Less than 0.10%
	PHYSICAL	TEST RESULTS	
Density	[kg/m³]	3100	No requirement
Specific Surface (Blaine)	[m²/kg]	461	No Requirement
Sieving Residue on 45 mic.	[%]	10.5	No Requirement
nitial setting time	[minutes]	151	Not less than 75 minutes
Final setting time	[minutes]	211	Not Requirement
Soundness (expansion)	[mm.]	1.0	Not more than 10 mm.
Compressive strength 2 days	[MPa]	16.0	More than 10 MPa.
Compressive strength 28 days*	[MPa]	36.2	Between 32.5 and 52.5 MPa

Remarks: *The 28 days strength is the average of previous month.

Wazo Hill, 2025/10/06th

Quality Control Manager

Board Directors: Hakan Gurdal (Turkish) Alfonso Velez (Spanish) Francesco Brambilla (Italian) Old Y M. 4. Plant Manager

Ruth Zaipuna (Tanzanian) Gary Whitehead (British) Oswald Urassa (Tanzanian)