

Heidelberg Materials

Tanzania Portland Cement Public Limited Company

P.O.Box 1950,Dar es Salaam-Tanzania Telephone: +255 746 810930 Fax: +255 746 810931

Info@twigacement.com www.twigacement.com

MONTHLY CERTIFICATE OF CHEMICAL & PHYSICAL TESTS TWIGA PLUS, CEM II/B-M CLASS 42.5 N AUGUST, 2025

Sampled and tested in accordance with the requirements of the Tanzanian Bureau of Standards

TZS 727-1/EAS 18-1. Equivalent to EN 197-1

	CHEMICAL T		
Test	Unit	Test results	Specified requirements
Loss on Ignition	[%]	6.97	No requirement
Insoluble Residues	[%]	1.45	Less than 5.0%
CaO	[%]	54.4	No requirement
SiO ₂	[%]	22.1	No requirement
CaO/SiO ₂	[-]	2.46	Not less than 2.0%
Al ₂ O ₃	[%]	5.80	No requirement
Fe ₂ O ₃	[%]	3,76	No requirement
MgO	[%]	1.56	Not more than 5.0%
SO ₃	[%]	2.52	Less than 3.5%
K ₂ O	[%]	0.44	No requirement
Na ₂ O	[%]	0.09	No requirement
P2O5	[%]	0,52	No requirement
ſiO ₂	[%]	0.87	No requirement
MnO	[%]	0.06	No requirement
Na ₂ O+ 0.658 K ₂ O)	[%]	0.38	No requirement
CI-	[%]	0.001	Less than 0.10%
	PHYSICAL TES		Less than 0.10 /8
Pensity	[kg/m3]	3100	No requirement
pecific Surface (Blaine)	[m²/kg]	475	No requirement
ieving Residue on 45 mic. mesh	[%]	8.1	No requirement
nitial Setting Time	[Minutes]	139	Not less than 60 minutes
inal Setting Time	[Minutes]	195	No requirement
oundness (Expansion)	[mm]	1.0	Not more than 10.0 mm
ompressive Strength 2 days	[MPa]	18.0	More than 10.0 MPa
ompressive Strength 28* *days*	[MPa]	44.3	Between 42.5 and 62.5 Mpa

Remarks: * The 28 days strength is the average of previous month.

1) 000

Wazo/HII. 2025/09/10

Quality Control Manager

Board Directors: Hakan Gurdal (Turkish) Alfonso Velez (Spanish) Francesco Brambilla (Italian)

Ruth Zaipuna (Tanzanian) Gary Whitehead (British) Oswald Urassa (Tanzanian) Commercial Director