



Heidelberg Materials

Tanzania Portland Cement Public Limited Company  
 P.O.Box 1950, Dar es Salaam-Tanzania  
 Telephone: +255 746 810930  
 Fax: +255 746 810931  
[info@twigacement.com](mailto:info@twigacement.com)  
[www.twigacement.com](http://www.twigacement.com)

## MONTHLY CERTIFICATE OF CHEMICAL AND PHYSICAL TESTS TWIGA EXTRA, CEM II/B-L CLASS 32.5 R FEBRUARY, 2026

Sampled and tested in accordance with the requirements of the Tanzanian Bureau of Standards  
 TZS 727-1/EAS 18-1. Equivalent to EN 197-1

CHEMICAL TEST RESULTS			
Test Parameters	Unit	Test results monthly average	Specified requirements
Loss on ignition	[%]	5.90	No Requirement
Insoluble Residue	[%]	1.22	Less than 5.0%
CaO	[%]	57.4	No Requirement
SiO <sub>2</sub>	[%]	21.5	No Requirement
CaO/SiO <sub>2</sub>	[-]	2.67	Not less than 2.0%
Al <sub>2</sub> O <sub>3</sub>	[%]	5.75	No Requirement
Fe <sub>2</sub> O <sub>3</sub>	[%]	3.83	No Requirement
MgO	[%]	1.53	Not more than 5.0%
SO <sub>3</sub>	[%]	2.58	Less than 3.5%
K <sub>2</sub> O	[%]	0.37	No Requirement
Na <sub>2</sub> O	[%]	0.10	No Requirement
P <sub>2</sub> O <sub>5</sub>	[%]	0.54	No Requirement
TiO <sub>2</sub>	[%]	0.61	No Requirement
MnO	[%]	0.03	No Requirement
(Na <sub>2</sub> O+0.658K <sub>2</sub> O)	[%]	0.35	No Requirement
Cl	[%]	0.002	Less than 0.10%
PHYSICAL TEST RESULTS			
Density	[kg/m <sup>3</sup> ]	3100	No requirement
Specific Surface (Blaine)	[m <sup>2</sup> /kg]	462	No Requirement
Sieving Residue on 45 mic.	[%]	12.4	No Requirement
Initial setting time	[minutes]	167	Not less than 75 minutes
Final setting time	[minutes]	203	Not Requirement
Soundness (expansion)	[mm.]	1.0	Not more than 10 mm.
Compressive strength 2 days	[MPa]	16.5	More than 10 MPa.
Compressive strength 28 days*	[MPa]	38.5	Between 32.5 and 52.5 MPa

Remarks: \*The 28 days strength is the average of previous month.

Wazo Hill, 2026/03/04<sup>th</sup>

  
 Quality Control Manager

  
 Plant Manager

  
 Commercial Director

Board Directors:  
 Hakan Gurdal (Turkish)  
 Alfonso Velez (Spanish)  
 Francesco Brambilla (Italian)

Ruth Zaipuna (Tanzanian)  
 Gary Whitehead (British)  
 Oswald Urassa (Tanzanian)