



Heidelberg Materials

Tanzania Portland Cement Public Limited Company

P.O.Box 1950, Dar es Salaam-Tanzania

Telephone: +255 746 810930

Fax: +255 746 810931

Info@twigacement.com

www.twigacement.com

MONTHLY CERTIFICATE OF CHEMICAL AND PHYSICAL TESTS
TWIGA EXTRA, CEM II/B-L CLASS 32.5 R
JULY, 2026

Sampled and tested in accordance with the requirements of the Tanzanian Bureau of Standards

TZS 727-1/EAS 18-1. Equivalent to EN 197-1

CHEMICAL TEST RESULTS			
Test Parameters	Unit	Test results monthly average	Specified requirements
Loss on ignition	[%]	7.34	No Requirement
Insoluble Residue	[%]	1.25	Less than 5.0%
CaO	[%]	56.7	No Requirement
SiO ₂	[%]	20.0	No Requirement
CaO/SiO ₂	[-]	2.84	Not less than 2.0%
Al ₂ O ₃	[%]	5.27	No Requirement
Fe ₂ O ₃	[%]	3.85	No Requirement
MgO	[%]	1.61	Not more than 5.0%
SO ₃	[%]	2.58	Less than 3.5%
K ₂ O	[%]	0.48	No Requirement
Na ₂ O	[%]	0.13	No Requirement
P ₂ O ₅	[%]	0.55	No Requirement
TiO ₂	[%]	0.64	No Requirement
MnO	[%]	0.05	No Requirement
(Na ₂ O+0.658K ₂ O)	[%]	0.44	No Requirement
Cl	[%]	0.002	Less than 0.10%
PHYSICAL TEST RESULTS			
Density	[kg/m ³]	3100	No requirement
Specific Surface (Blaine)	[m ² /kg]	453	No Requirement
Sieving Residue on 45 mic.	[%]	9.6	No Requirement
Initial setting time	[minutes]	167	Not less than 75 minutes
Final setting time	[minutes]	269	Not Requirement
Soundness (expansion)	[mm.]	1.0	Not more than 10 mm.
Compressive strength 2 days	[MPa]	18.8	More than 10 MPa.
Compressive strength 28 days*	[MPa]	46.7	Between 32.5 and 52.5 MPa

Remarks: *The 28 days strength is the average of previous month.

Wazo Hills 2026/07/03rd

Quality Control Manager

Plant Manager

Commercial Director

Board Directors:

Hakan Gurdal (Turkish)

Alfonso Velez (Spanish)

Francesco Brambilla (Italian)

Ruth Zeipuna (Tanzanian)

Gary Whitehead (British)

Oswald Urassa (Tanzanian)