



Heidelberg Materials

Tanzania Portland Cement Public Limited Company

P.O.Box 1950, Dar es Salaam-Tanzania

Telephone: +255 746 810930

Fax: +255 746 810931

info@twigacement.com

www.twigacement.com

MONTHLY CERTIFICATE OF CHEMICAL & PHYSICAL TESTS
TWIGA PLUS RAPID, CEM II/B-L CLASS 42.5 R
AUGUST, 2026

Sampled and tested in accordance with the requirements of the Tanzanian Bureau of Standards
TZS 727-1/EAS 18-1. Equivalent to EN 197-1

CHEMICAL TEST RESULTS

Test	Unit	Test results	Specified requirements
Loss on Ignition	[%]	6.11	No requirement
Insoluble Residues	[%]	1.42	Less than 5.0%
CaO	[%]	56.6	No requirement
SiO ₂	[%]	21.0	No requirement
CaO/SiO ₂	[-]	2.69	Not less than 2.0%
Al ₂ O ₃	[%]	5.53	No requirement
Fe ₂ O ₃	[%]	3.89	No requirement
MgO	[%]	1.70	Not more than 5.0%
SO ₃	[%]	2.52	Less than 3.5%
K ₂ O	[%]	0.47	No requirement
Na ₂ O	[%]	0.18	No requirement
P ₂ O ₅	[%]	0.61	No requirement
TiO ₂	[%]	0.73	No requirement
MnO	[%]	0.05	No requirement
(Na ₂ O+ 0.658 K ₂ O)	[%]	0.49	No requirement
Cl ⁻	[%]	0.001	Less than 0.10%

PHYSICAL TEST RESULTS

Density	[kg/m ³]	3100	No requirement
Specific Surface (Blaine)	[m ² /kg]	451	No requirement
Sieving Residue on 45 mic. mesh	[%]	7.4	No requirement
Initial Setting Time	[Minutes]	157	Not less than 60 minutes
Final Setting Time	[Minutes]	265	No requirement
Soundness (Expansion)	[mm]	1.0	Not more than 10.0 mm
Compressive Strength 2 days	[MPa]	20.5	More than 10.0 MPa
Compressive Strength 28* *days*	[MPa]	48.7	Between 42.5 and 62.5 Mpa

Remarks: * The 28 days strength is the average of previous month.

Wazo Hill, 2026/09/04th


Quality Control Manager


Plant Manager


Commercial Director

Board Directors:

Hakan Cural (Turkish)
Alfonso Velez (Spanish)
Francesco Brambilla (Italian)

Ruth Zepura (Tanzanian)
Gary Whiteneed (British)
Oswald Urassa (Tanzanian)